

CERTIFICATE OF MAILING

I hereby certify that this correspondence is being deposited with the United States Postal Service as First Class Mail in an envelope addressed to:

"Assistant Commissioner for Patents
Washington, D.C. 20231"

on April 6, 2004

Rimma Mitelman 04/06/04
RIMMA MITELMAN Date of
Reg. No. 34,396 Signature
Attorney for Applicant(s)

PATENT
#02-0532-UNI
Case #C4277(C)

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant: Macnab et al.
Serial No.: 10/734,756
Filed: December 11, 2003
For: POLYMERS AND LAUNDRY DETERGENT COMPOSITIONS CONTAINING THEM

Edgewater, New Jersey 07020
April 6, 2004

SUBMISSION OF PRIORITY DOCUMENT

Assistant Commissioner for Patents
Washington, D.C. 20231

Sir:

Pursuant to rule 55(b) of the Rules of Practice in Patent Cases, Applicant(s) is/are submitting herewith a certified copy of the United Kingdom Application No. 0229146.6 filed December 13, 2002, upon which the claim for priority under 35 U.S.C. § 119 was made in the United States.

It is respectfully requested that the priority document be made part of the file history.

Respectfully submitted,

Rimma Mitelman
Rimma Mitelman
Registration No. 34,396
Attorney for Applicant(s)

RM/mt
(201) 840-2671





INVESTOR IN PEOPLE

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.




Signed

Stephen Hordley

Dated

27 October 2003





The
Patent
Office

16DEC02 E770989-1 002898
P01/7700 0.00-0229146.6

The Patent Office

Cardiff Road
Newport
Gwent NP10 8QQ

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

1. Your reference

C4277(C)/sje

2. Patent application number
(The Patent Office will fill in this part)

0229146.6

13 DEC 2002

3. Full name, address and postcode of the or of each applicant (underline all surnames)

UNILEVER PLC
UNILEVER HOUSE, BLACKFRIARS
LONDON, EC4P 4BQ

Patents ADP number (if you know it)

50426956002

If the applicant is a corporate body, give the country/state of its incorporation

UNITED KINGDOM

4. Title of the invention

POLYMERS AND LAUNDRY
DETERGENT COMPOSITIONS CONTAINING
THEM

5. Name of your agent (if you have one)

PETER WILLIAM ELLIOTT
~~FRANSELLA Mary Evelyn~~

"Address for Service" in the United Kingdom to which all correspondence should be sent (including the postcode)

PATENT DEPARTMENT, UNILEVER PLC
COLWORTH HOUSE, SHARNBROOK
BEDFORD, MK44 1LQ

Patents ADP number (if you know it)

5995477002

~~50740687221~~

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country	Priority application number (if you know it)	Date of filing (day / month / year)
---------	---	--

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application	Date of filing (day/month/year)
-------------------------------	------------------------------------

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

- a) any applicant named in part 3 is not an inventor, or
 - b) there is an inventor who is not named as an applicant, or
 - c) any named applicant is a corporate body.
- See note (d))

YES

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description	24
Claim(s)	6
Abstract	1
Drawing(s)	-

10. If you are also filing any of the following, state how many against each item.

Priority Documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

Request for preliminary examination and search (Patents Form 9/77)

1

Request for substantive examination (Patents Form 10/77)

Any other documents (please specify)

11.

I/We request the grant of a patent on the basis of this application.

Signature(s)



Date: 13-Dec-02

Sandra Jane EDWARDS, Authorised Signatory

12. Name and daytime telephone number of person to contact in the United Kingdom

Sandra Edwards, Tel 01234 22 2068

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

POLYMERS AND LAUNDRY DETERGENT COMPOSITIONS CONTAINING THEMTECHNICAL FIELD

5

The present invention relates to laundry detergent compositions containing certain vinyl pyrrolidone copolymers. The compositions exhibit improved detergency on oily and clay soils and reduced soil redeposition during the wash.

BACKGROUND AND PRIOR ART

15 Polyvinyl pyrrolidone (PVP) and some related polymers are known ingredients of laundry detergent compositions, providing the benefit of reduced dye transfer between fabrics in a mixed load.

20 Laundry detergent compositions containing PVP as a dye transfer inhibitor are disclosed, for example, in WO 92 18597A and WO 95 27028A (Procter & Gamble).

GB 1 354 498 (Unilever) discloses laundry detergent
25 compositions containing vinyl pyrrolidone/vinyl acetate (PVP/VA) random copolymers as antiredeposition agents. PVP itself is stated to be ineffective.


Other vinyl pyrrolidone copolymers are known for cosmetic
30 and agricultural applications.

DEFINITION OF THE INVENTION

In a first aspect, the present invention provides a laundry detergent composition comprising an organic surfactant, and
5 a hydrophobically modified vinyl pyrrolidone polymer which is a copolymer having a vinyl pyrrolidone backbone and pendant hydrophobic side chains, the polymer being present in an amount effective to improve detergency and/or antiredeposition.

10

In a second aspect, the invention provides a class of novel hydrophobically modified vinyl pyrrolidone polymers which are copolymers having a vinyl pyrrolidone backbone and
15 pendant hydrophobic side chains derived from a vinyl ester of the general formula I:



wherein R^1 is a linear or branched alkyl group having from 4
20 to 16 carbon atoms.


In a third aspect, the invention provides the use of a hydrophobically modified vinyl pyrrolidone polymer to improve the detergency and/or antiredeposition of a built
25 laundry detergent composition.

The hydrophobically modified vinyl pyrrolidone polymer

30 The polymer used in the detergent compositions of the invention is a polyvinyl pyrrolidone modified by the

inclusion of hydrophobic units as pendant side chains. The polymer is a copolymer of vinyl pyrrolidone (VP), providing the polymer backbone, and a hydrophobic monomer.

5 Vinyl pyrrolidone has the formula



The hydrophobic side chains preferably comprise alkyl chains containing from 4 to 20 carbon atoms.

First preferred embodiment

According to a first preferred embodiment of the invention, the polymer is an alkylated vinyl pyrrolidone polymer wherein the alkyl chains contain from 4 to 20 carbon atoms.

In this embodiment of the invention, the hydrophobic side chains are derived from a hydrophobic comonomer which is an olefin containing from 4 to 20 carbon atoms.

Preferably the polymer contains from 10 to 90 mole% of vinyl pyrrolidone (VP) units and from 10 to 90 mole% of hydrophobic comonomer units.

Suitable polymers are commercially available from International Specialty Products (ISP) as the Ganex (Trade Mark), Antaron (Trade Mark) and Agrimer (Trade Mark) series. They may be prepared by chemical modification of PVP with long-chain alpha-olefins. Examples are shown in the Table below.


Polymer trade name	Alkyl chain	Comonomer (olefin)	Mole ratio VP:olefin	Physical form
Agrimer AL-10 Ganex P904LC Antaron P904	C ₄	Butene	90:10	Water-soluble powder
Ganex V216 Antaron V216	C ₁₆	Hexadecene	20:80	Water-insoluble wax
Ganex V516 Antaron V516	C ₁₆	Hexadecene	50:50	Water-insoluble wax

These polymers are marketed for use in cosmetic and personal care compositions, and for agricultural purposes as ingredients in crop treatment compositions.

Second preferred embodiment

According to a second preferred embodiment of the invention, the hydrophobically modified vinyl pyrrolidone polymer has pendant hydrophobic side chains which are alkyl chains having from 4 to 20 carbon atoms linked to the vinyl pyrrolidone backbone by an ester linkage.

The hydrophobic monomer precursor of the side chains is preferably a vinyl ester of the general formula I:



wherein R^1 is a linear or branched alkyl group having from 4 to 16 carbon atoms.


In the general formula I, R^1 is preferably a linear or branched alkyl group having from 6 to 10 carbon atoms.

More preferably, R^1 is a group of the formula II




wherein R^2 is a linear alkyl group having from 2 to 8 carbon atoms and R^3 is a methyl or ethyl group.

Most preferably, the hydrophobic comonomer of the formula I is vinyl 2-ethylhexanoate:



The polymer preferably contains from 90 to 99.5 wt% of vinyl pyrrolidone monomer units and from 0.5 to 10 wt% of vinyl 2-ethyl hexanoate monomer units.

Copolymers of vinyl pyrrolidone and vinyl 2-ethylhexanoate have the general formula III




20 Preparation of the polymers having an ester linkage

These polymers may be prepared by free radical polymerisation.

25 A process suitable for preparing these polymers is disclosed in US 5 319 041 (Zhong et al) which describes the synthesis of copolymers of vinylpyrrolidone and vinyl acetate. An alternative process is disclosed in US 5 122 582 (Porthoff-Karl).

Accordingly, a further aspect of the present invention provides a process for the preparation of a hydrophobically modified vinyl pyrrolidone polymer which is a copolymer having a vinyl pyrrolidone backbone and pendant hydrophobic
5 side chains, wherein the hydrophobic side chains of the copolymer are derived from a vinyl ester of the general formula I:



10

wherein R^1 is a linear or branched alkyl group having from 4 to 16 carbon atoms,

which process comprises reacting vinyl pyrrolidone with a
15 monomer of the formula I in the presence of a free radical initiator.

The laundry detergent composition

20

In the detergent composition of the invention, the polymer is present in an amount sufficient to enhance detergency and/or antiredeposition. Suitably the polymer is present in an amount of from 0.5 to 5 wt%, preferably from 1 to
25 4 wt%.

The detergent composition may suitably comprise:

- (a) from 5 to 60 wt%, preferably from 10 to 40 wt%, of organic surfactant,
 - 30 (b) optionally from 5 to 80 wt%, preferably from 10 to 60 wt%, of detergency builder,
-

- (c) from 0.5 to 5 wt%, preferably from 1 to 4 wt%, of the hydrophobically modified vinyl pyrrolidone polymer,
(d) optionally other detergent ingredients to 100 wt%.

5

The organic surfactant

The compositions of the invention may contain any organic surfactants (detergent-active compounds) suitable for
10 incorporation into laundry detergent compositions.

Detergent-active compounds (surfactants) may be chosen from soap and non-soap anionic, cationic, nonionic, amphoteric and zwitterionic detergent-active compounds, and mixtures
15 thereof. Many suitable detergent-active compounds are available and are fully described in the literature, for example, in "Surface-Active Agents and Detergents", Volumes I and II, by Schwartz, Perry and Berch. The preferred detergent-active compounds that can be used are soaps and
20 synthetic non-soap anionic and nonionic compounds. The total amount of surfactant present is suitably within the range of from 5 to 60 wt%, preferably from 5 to 40 wt%.

Anionic surfactants are well-known to those skilled in the
25 art. Examples include alkylbenzene sulphonates, particularly linear alkylbenzene sulphonates having an alkyl chain length of C₈-C₁₅; primary and secondary alkylsulphates, particularly C₈-C₂₀ primary alkyl sulphates; alkyl ether sulphates; olefin sulphonates; alkyl xylene
30 sulphonates; dialkyl sulphosuccinates; and fatty acid ester sulphonates. Sodium salts are generally preferred.

Nonionic surfactants that may be used include the primary and secondary alcohol ethoxylates, especially the C₈-C₂₀ aliphatic alcohols ethoxylated with an average of from 1 to 20 moles of ethylene oxide per mole of alcohol, and more especially the C₁₀-C₁₅ primary and secondary aliphatic alcohols ethoxylated with an average of from 1 to 10 moles of ethylene oxide per mole of alcohol. Non-ethoxylated nonionic surfactants include alkylpolyglycosides, glycerol monoethers, and polyhydroxyamides (glucamide).

10

Cationic surfactants that may be used include quaternary ammonium salts of the general formula $R_1R_2R_3R_4N^+ X^-$ wherein the R groups are long or short hydrocarbyl chains, typically alkyl, hydroxyalkyl or ethoxylated alkyl groups, and X is a solubilising anion (for example, compounds in which R₁ is a C₈-C₂₂ alkyl group, preferably a C₈-C₁₀ or C₁₂-C₁₄ alkyl group, R₂ is a methyl group, and R₃ and R₄, which may be the same or different, are methyl or hydroxyethyl groups); and cationic esters (for example, choline esters).

20

According to a preferred embodiment of the invention, the composition comprises a sulphonate anionic surfactant. According to an especially preferred embodiment, the sulphonate anionic surfactant comprises linear alkylbenzene sulphonate (LAS).

25

An especially favourable interaction between LAS and the hydrophobically modified vinyl pyrrolidone polymer has been observed, giving improved primary detergency on difficult oily and particulate soils such as dirty motor oil and mud, and reduced redeposition of soil onto the washload during

30

the wash (sometimes referred to as secondary detergency). Without being bound by theory, it is postulated that the this benefit may be attributed to a reduction in the critical micelle concentration (CMC) of the LAS.

- 5 Preferably, the compositions contains from 3 to 30 wt%, more preferably from 10 to 25 wt%, of LAS.

The optional detergency builder

10

Preferably, the detergent compositions of the invention also contain one or more detergency builders. The total amount of detergency builder in the compositions may suitably range from 5 to 80 wt%, preferably from 10 to 60 wt%.

15

Preferred builders are alkali metal aluminosilicates, more especially crystalline alkali metal aluminosilicates (zeolites), preferably in sodium salt form.

- 20 Zeolite builders may suitably be present in a total amount of from 5 to 60 wt%, preferably from 10 to 50 wt%.

The zeolites may be supplemented by other inorganic builders, for example, amorphous aluminosilicates, or

- 25 layered silicates such as SKS-6 ex Clariant.

The zeolites may be supplemented by organic builders, for example, polycarboxylate polymers such as polyacrylates and acrylic/maleic copolymers; monomeric polycarboxylates such
30 as citrates, gluconates, oxydisuccinates, glycerol mono-, di- and trisuccinates, carboxymethyloxysuccinates,

- 11 -

carboxymethyloxymalonates, dipicolinates, hydroxyethyliminodiacetates, alkyl- and alkenylmalonates and succinates; and sulphonated fatty acid salts.

- 5 Alternatively, the compositions of the invention may contain phosphate builders, for example, sodium tripolyphosphate.

Especially preferred organic builders are citrates, suitably used in amounts of from 1 to 30 wt%, preferably from 2 to
10 15 wt%; and acrylic polymers, more especially acrylic/maleic copolymers, suitably used in amounts of from 0.5 to 15 wt%, preferably from 1 to 10 wt%. Builders, both inorganic and organic, are preferably present in alkali metal salt, especially sodium salt, form.

15

According to a preferred embodiment of the invention, the detergency builder, which is present in an amount of from 5 to 80 wt%, preferably from 10 to 60 wt%, is selected from sodium tripolyphosphate, zeolites, sodium carbonate and
20 mixtures thereof.

Other detergent ingredients

- 25 Detergent compositions according to the invention may also suitably contain a bleach system. Preferably this will include a peroxy bleach compound, for example, an inorganic persalt or an organic peroxyacid, capable of yielding hydrogen peroxide in aqueous solution.

30

Preferred inorganic persalts are sodium perborate
monohydrate and tetrahydrate, and sodium percarbonate, the
latter being especially preferred. The sodium percarbonate
may have a protective coating against destabilisation by
5 moisture. The peroxy bleach compound is suitably present in
an amount of from 5 to 35 wt%, preferably from 10 to 25 wt%.

The peroxy bleach compound may be used in conjunction with a
bleach activator (bleach precursor) to improve bleaching
10 action at low wash temperatures. The bleach precursor is
suitably present in an amount of from 1 to 8 wt%, preferably
from 2 to 5 wt%. Preferred bleach precursors are
peroxycarboxylic acid precursors, more especially peracetic
acid precursors and peroxybenzoic acid precursors; and
15 peroxycarbonic acid precursors. An especially preferred
bleach precursor suitable for use in the present invention
is N,N,N',N'-tetracetyl ethylenediamine (TAED).

A bleach stabiliser (heavy metal sequestrant) may also be
20 present. Suitable bleach stabilisers include
ethylenediamine tetraacetate (EDTA), diethylenetriamine
pentaacetate (DTPA), ethylenediamine disuccinate (EDDS),
and the polyphosphonates such as the Dequests (Trade Mark),
ethylenediamine tetramethylene phosphonate (EDTMP) and
25 diethylenetriamine pentamethylene phosphate (DETPMP).

The compositions of the invention may contain alkali metal,
preferably sodium, carbonate, in order to increase
detergency and ease processing. Sodium carbonate may
30 suitably be present in amounts ranging from 1 to 60 wt%,
preferably from 2 to 40 wt%.

As previously indicated, sodium silicate may also be present. The amount of sodium silicate may suitably range from 0.1 to 5 wt%. Sodium silicate, as previously indicated, is preferably introduced via the second base granule.

Powder flow may be improved by the incorporation of a small amount of a powder structurant. Examples of powder structurants, some of which may play other roles in the formulation as previously indicated, include, for example, fatty acids (or fatty acid soaps), sugars, acrylate or acrylate/maleate polymers, sodium silicate, and dicarboxylic acids (for example, Sokalan (Trade Mark) DCS ex BASF). One preferred powder structurant is fatty acid soap, suitably present in an amount of from 1 to 5 wt%.

Other materials that may be present in detergent compositions of the invention include antiredeposition agents such as cellulosic polymers; soil release agents; anti-dye-transfer agents; fluorescers; inorganic salts such as sodium sulphate; enzymes (proteases, lipases, amylases, cellulases); dyes; coloured speckles; perfumes; and fabric conditioning compounds. This list is not intended to be exhaustive.

Product form and preparation

The compositions of the invention may be of any suitable physical form, for example, particulates (powders, granules, tablets), liquids, pastes, gels or bars.

According to one especially preferred embodiment of the invention, the detergent composition is in particulate form.

5 Powders of low to moderate bulk density may be prepared by spray-drying a slurry, and optionally postdosing (dry-mixing) further ingredients. "Concentrated" or "compact" powders may be prepared by mixing and granulating processes, for example, using a high-speed mixer/granulator, or other non-tower processes.

10

Tablets may be prepared by compacting powders, especially "concentrated" powders.

15 Also preferred are liquid detergent compositions, which may be prepared by admixing the essential and optional ingredients in any desired order to provide compositions containing the ingredients in the requisite concentrations.

20 Incorporation of the hydrophobically modified vinyl pyrrolidone polymer

The polymers may be incorporated at any suitable stage in the manufacture of the compositions of the invention.

25

For example, in the manufacture of spray-dried particulate compositions, polymer in powder or solution (preferably aqueous) form may be incorporated in the slurry. For non-tower particulates, polymer powder or solution may be easily
30 introduced into mixing and granulating apparatus, either

alone or in admixture with other solid or liquid ingredients
as appropriate.

5 EXAMPLES

The invention is further illustrated by the following
Examples, in which parts and percentages are by weight
unless otherwise stated.

10

EXAMPLES 1 to 4

Preparation of vinyl pyrrolidone/vinyl 2-ethylhexanoate
copolymers

15

The following copolymers were prepared by free radical
polymerisation. The preparation was adapted from the
process described in US 5 319 041 (Zhong et al).

20

Example	Weight% vinyl pyrrolidone	Weight% vinyl 2-ethyl hexanoate
1	99	1
2	98	2
3	96	4
4	92	8

The starting materials used were as follows (* denotes Trade Mark):

Name	Chemical name	Supplier	Function
VP	Vinylpyrrolidone	Aldrich	Monomer
V2EH	Vinyl 2-ethylhexanoate	Aldrich	Monomer
Vazo* 67	2,2-azobis(2-methylbutyronitrile)	Fluka	Initiator
Luperox* 101	2.5-bis(tert-butylperoxy) - 2.5-dimethylhexane	Aldrich	Initiator
Butanol	n-Butanol		Solvent

5

Experimental procedure

The polymers were prepared using a four-step procedure as described below.

10

The relative weights of VP and V2EH required were calculated in function of the % of hydrophobic units needed in the final copolymer. For example, the total quantities required to make a 200 g batch of the polymer of Example 1

15 are as follows:

Addition Step/Reagent	VP (g)	V2EH (g)	VAZO*67 (g)	Luperox*101 (g)	Butanol (g)
1	19.8	0.25	0.0312	0.0312	20.05
2	-	-	0.2688	0.2688	2
3	59.4	0.75	-	-	60.15
4	19.8	-	-	-	19.8
Total amounts (g)	99	1	0.3	0.3	102

Four-step process

5

A first mixture was prepared to the following composition:

VP	20% of total weight of monomers
V2EH	25% of total weight of monomers
Vazo* 67	10.4% of 0.3% of total weight of monomers (VP + V2EH)
Luperox* 101	10.4% of 0.3% of total weight of monomers (VP + V2EH)
Butanol	Amount equal to total weight of VP + V2EH in this mixture

- 10 The monomers were charged under a blanket of nitrogen in a 125 mL four-neck flask equipped with a compressed air stirrer, reflux condenser and thermometer. The components were stirred for about 10 minutes and heated to 85°C.

Then a second mixture having the following composition:

Vazo* 67	89.6% of 0.3% of total weight of monomers (VP + V2EH)
Luperox* 101	89.6% of 0.3% of total weight of monomers (VP + V2EH)
Butanol	2 g

was added over a period of 30 minutes.

5

A third mixture of having the following composition:

VP	60% of total weight of VP
V2EH	75% of total weight of V2EH
Butanol	100% of total weight of VP and V2EH of third mixture

was then gradually added over a period of 40 minutes..

10

Upon completion of V2EH monomer addition, a fourth mixture having the following composition:

VP	20% of total weight of VP
Butanol	100% of weight of VP of fourth mixture

15 was added over a period of 15 min.

After the above additions were completed, the temperature was increased to 117°C for 3 hours. The reactor contents were then cooled to room temperature.

- 5 The copolymers were characterised by means of proton NMR spectroscopy and gel permeation chromatography.

Example 5

10 Detergency/antiredeposition performance

Detergency and antiredeposition performance of the polymers were evaluated by a small scale wash method, using a laundry detergent composition having the following formulation:

15

	Weight%
Linear alkylbenzene sulphonate	6.00
Sodium C ₁₂ -C ₁₄ alcohol ethoxy sulphate 3EO	10.50
Nonionic surfactant (C ₁₂ -C ₁₄ alcohol ethoxylate, 9EO)	6.60
Sodium citrate dihydrate	3.20
Propylene glycol	4.75
Sorbitol	3.25
Sodium borate pentahydrate	2.13
(Water to	100.00)

Methodology

The polymers were tested for their ability to enhance the removal of oily and clay/sebum soil from white cotton
5 fabric, using an apparatus for simulating a soiling and wash procedure on a small scale.

Using this apparatus, the fabric was soiled, and subjected to a simulated main wash procedure using wash liquors with
10 and without the polymer according to the invention.

The apparatus

15 The wash apparatus used allows different liquids to be simultaneously contacted with different regions of a single sheet of fabric. The fabric sheet is clamped between an upper and lower block. The fabric sheet is sandwiched between two rubber seals. Both blocks and seals contain an
20 8 x 12 array of square cavities, which are aligned. When blocks and fabrics are clamped together, liquids placed in individual wells do not leak or bleed through to other wells, due to the pressure applied by the blocks in the regions separating the wells. The liquids are forced to
25 flow back and forth through the fabric by means of a pneumatically actuated thin rubber membrane, which is placed between the fabrics and the lower block. Repeated flexing of the membrane away from and towards the fabrics results in fluid motion through the fabrics.

Soiling

For the oily soil evaluation, the dry fabric was placed on top of a 96 well polypropylene microtitre plate. Oily soil
5 (5 μ L of dirty motor oil (15% weight in toluene)) was dispensed from a pipette, onto the centre of each of the 96 cells on the cloth. The stained fabrics were allowed to dry at room temperature for 24 hours.

10 For clay/sebum soiling a standard cotton test cloth (AS9) was used.

Wash

15

The test fabric was then clamped in the washing apparatus, 200 μ L doses of each wash solution were placed in appropriate wells. The liquids flowed through the fabrics for 20 minutes, at 30 °C with a flow cycle time of 1.5
20 seconds. After 20 minutes, the free liquid in the cells was poured off. The blocks were then separated and the fabric removed, and thoroughly rinsed for 1 minute in 200 mL demineralised water. The fabrics were allowed to dry for 24 hours. Reflectance (ΔE or ΔR) was then measured.

25

Experimental conditions

The experiments were carried out at product doses of 0.1,
30 0.5 and 1.5 g/L, in water of 3° and 12° FH, the hardness being made up of three parts calcium to 1 part magnesium.

The polymers were dosed separately at levels of 0.05, 0.1 and 0.5 g/l, and there was also a polymer-free control for each set of conditions.

- 5 For the tests using oily soil (dirty motor oil), the results are expressed as SRI (soil release index), where
- $$\text{SRI} = 100 - \Delta E$$

- 10 For the tests using clay/sebum soil, the results are expressed as ΔR (image analysis, equivalent to ΔR at 460 nm).

Results for the polymer of Example 4Clay/sebum soil

Water hardness (°F)	Product dose g/L	ΔR (460 nm) for polymer concentrations of		
		0 (control)	0.05	0.5
0.1	3	4.01	4.13	4.37
0.5	3	3.99	4.36	4.72
1.5	3	4.60	5.44	5.72
0.1	12	3.50	4.00	3.84
0.5	12	3.67	4.01	3.99
1.5	12	3.94	4.36	4.80

5

Oily soil (dirty motor oil)

10

Water hardness (°F)	Product dose g/L	SRI for polymer concentrations of			
		0 (control)	0.05	0.1	0.5
0.1	3	71.31	71.82	71.78	71.92
0.5	3	72.20	72.58	72.21	72.36
1.5	3	72.99	74.01	73.17	73.59
0.1	12	71.16	71.49	71.13	71.88
0.5	12	71.94	72.66	72.14	72.15
1.5	12	73.10	74.49	73.59	74.19

Averaged results for the polymers of Examples 1-4

5 The following table shows the results for all four polymers
on oily soil (dirty motor oil) averaged over all product
levels (0.1, 0.5 and 1.5 g/l), polymer levels (0.05, 0.1 and
0.5 g/l), and water hardnesses (3 and 12°FH).

10 The results are expressed as reflectance increases (ΔR)
compared with a control containing no polymer. All results
represent a significant difference at 95%.

Polymer of Example	Mean ΔR
1	0.49
2	0.36
3	0.46
4	0.51

15

*

*

*

20

CLAIMS

1 A laundry detergent composition comprising an organic
5 surfactant, and a hydrophobically modified vinyl pyrrolidone
polymer which is a copolymer having a vinyl pyrrolidone
backbone and pendant hydrophobic side chains, the polymer
being present in an amount effective to improve detergency
and/or antiredeposition.

10

2 A detergent composition as claimed in claim 1, wherein
the polymer has pendant hydrophobic side chains comprising
alkyl chains containing from 4 to 20 carbon atoms.

15


3 A detergent composition as claimed in claim 2, wherein
the polymer has pendant hydrophobic side chains derived from
olefins containing from 4 to 20 carbon atoms.

20

4 A detergent composition as claimed in claim 3, wherein
the polymer contains from 10 to 90 mole% of vinyl
pyrrolidone units and from 10 to 90 mole% of hydrophobic
25 comonomer units.

5 A detergent composition as claimed in claim 1 or claim
2, wherein the polymer has pendant hydrophobic side chains
which are alkyl chains having from 4 to 20 carbon atoms
30 linked to the vinylpyrrolidone backbone by an ester linkage.

6 A detergent composition as claimed in claim 5, wherein the pendant hydrophobic side chains of the copolymer are derived from a vinyl ester of the general formula I:




wherein R^1 is a linear or branched alkyl group having from 4 to 16 carbon atoms.

10

7 A detergent composition as claimed in claim 6, wherein in the general formula I R^1 is a linear or branched alkyl group having from 6 to 10 carbon atoms.

15

8 A detergent composition as claimed in claim 7, wherein in the general formula I R^1 is a group of the formula II



wherein R^2 is a linear alkyl group having from 2 to 8 carbon atoms and R^3 is a methyl or ethyl group.

25

9 A detergent composition as claimed in claim 8, wherein the polymer contains units derived from vinyl 2-ethylhexanoate.

30

10 A detergent composition as claimed in claim 9, wherein
the polymer contains from 90 to 99.5 wt% of vinyl
pyrrolidone monomer units and from 0.5 to 10 wt% of vinyl
2-ethylhexanoate monomer units.

5

11 A detergent composition as claimed in any preceding
claim, which contains from 0.5 to 5 wt%, preferably from 1
to 4 wt%, of the hydrophobically modified vinyl pyrrolidone
10 polymer.

12 A detergent composition as claimed in any preceding
claim, which comprises:

- 15 (a) from 5 to 60 wt%, preferably from 10 to 40 wt%, of
organic surfactant,
(b) optionally from 5 to 80 wt%, preferably from 10 to
60 wt%, of detergency builder,
(c) from 0.5 to 5 wt%, preferably from 1 to 4 wt%, of the
20 hydrophobically modified vinyl pyrrolidone polymer,
(d) optionally other detergent ingredients to 100 wt%.

13 A detergent composition as claimed in any preceding
25 claim, wherein the organic surfactant (a) comprises a
sulphonate anionic surfactant.


14 A detergent composition as claimed in claim 13, wherein
30 the organic surfactant (a) comprises linear alkylbenzene
sulphonate.

15 A detergent composition as claimed in claim 14, which
contains from 3 to 30 wt%, preferably from 10 to 25 wt%, of
5 linear alkylbenzene sulphonate.

16 A detergent composition as claimed in any preceding
claim, which comprises from 5 to 80 wt%, preferably from 10
10 to 60 wt%, of detergency builder selected from sodium
tripolyphosphate, zeolites, sodium carbonate and mixtures
thereof.

15 17 Use of a hydrophobically modified vinyl pyrrolidone
copolymer to improve the detergency and/or antiredeposition
of a laundry detergent composition.

18 A hydrophobically modified vinyl pyrrolidone polymer
which is a copolymer having a vinyl pyrrolidone backbone and
pendant hydrophobic side chains, wherein the hydrophobic
side chains of the copolymer are derived from a vinyl ester
5 of the general formula I:



wherein R^1 is a linear or branched alkyl group having from 4
10 to 16 carbon atoms.

19 A polymer as claimed in claim 18, wherein in the
general formula I R^1 is a linear or branched alkyl group
15 having from 6 to 10 carbon atoms.

20 A polymer as claimed in claim 19, wherein in the
general formula I R^1 is a group of the formula II
20



25 wherein R^2 is a linear alkyl group having from 2 to 8 carbon
atoms and R^3 is a methyl or ethyl group.


21 A polymer as claimed in claim 20, which contains units
30 derived from vinyl 2-ethylhexanoate.

22 A polymer as claimed in claim 21, which contains from
90 to 99.5 wt% of vinyl pyrrolidone monomer units and from
0.5 to 10 wt% of vinyl 2-ethylhexanoate monomer units.

5

23 A process for the preparation of a polymer as claimed
in any one of claims 18 to 22, which comprises reacting
vinyl pyrrolidone and a vinyl ester of the general formula
I:

10



wherein R^1 is a linear or branched alkyl group having from 4
to 16 carbon atoms, in the presence of a free radical
initiator.

20

*

*

*

ABSTRACT

5 Hydrophobically modified vinyl pyrrolidone polymers which
are copolymers having a vinyl pyrrolidone backbone and
pendant hydrophobic side chains are useful in laundry
detergent compositions to improve detergency and/or
antiredeposition. The pendant hydrophobic side chains
10 preferably comprise alkyl chains containing from 4 to 20
carbon atoms and may be linked to the backbone via an ester
linkage. A preferred class of novel polymers is comprised
by copolymers of vinylpyrrolidone and
vinyl 2-ethylhexanoate.

15

